

MHB60 STAINLESS STEEL METAL HOSE - DOUBLE BRAID



Tube: 316 corrugated stainless steel
Reinforcement: 304 stainless steel single and double braid
Application: For use with petroleum, chemical, steel, and power generation plants. Can also be used in heating, pump, ventilation, and air conditioning systems. It is designed for hot or cold media transfers, such as hot oil and lube oil transfers. Can also be used for jump lines and loading arms or terminal loading/off loading products.

METAL HOSE ASSEMBLIES - 316 STAINLESS WETTED PARTS



Floating x Floating

Part Number	Hose Size	Length	Fitting A	Fitting B	Max WP	Weight / Assy
		ft			psi	lbs
MHB60-200-10	2"	10	Floating	Floating	865	44.0
MHB60-200-20	2"	20	Floating	Floating	865	76.0
MHB60-300-10	3"	10	Floating	Floating	523	61.0
MHB60-300-20	3"	20	Floating	Floating	523	103.0
MHB60-400-10	4"	10	Floating	Floating	455	98.0
MHB60-400-20	4"	20	Floating	Floating	455	163.0
MHB60-600-10	6"	10	Floating	Floating	320	163.0
MHB60-600-20	6"	20	Floating	Floating	320	277.0
MHB60-800-10	8"	10	Floating	Floating	387	251.0
MHB60-800-20	8"	20	Floating	Floating	387	421.0
MHB60-1000-10	10"	10	Floating	Floating	368	267.0
MHB60-1000-20	10"	20	Floating	Floating	368	423.0
MHB60-1200-10	12"	10	Floating	Floating	273	353.0
MHB60-1200-20	12"	20	Floating	Floating	273	551.00

*Built with 304 stainless steel 150lb floating x floating flanges
 See derating chart page 56.

METAL HOSE TEMPERATURE DERATING

To calculate a working pressure derated for elevated temperature, multiply the hose working pressure shown in the catalog by the appropriate derating factor below.

Note: The working pressure of an assembly at elevated temperatures may be affected by fitting type, material and method of attachment.

10

Metal Hose

Temp Deg °F	T304 T301*	T304L	T316	T316L	T321	T430	Copper	CS76	"Monel 400 & C22"	Inconel 600	Inconel 625	Carbon Steel*	Alum. 3003 H14
100	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00
200	1.00	1.00	1.00	1.00	1.00	1.00	0.80	1.00	0.88	1.00	1.00	1.00	1.00
300	1.00	1.00	1.00	1.00	1.00	0.98	0.78	1.00	0.82	1.00	1.00	1.00	0.64
400	0.95	0.93	0.97	0.93	1.00	0.96	0.50	1.00	0.79	1.00	1.00	1.00	0.34
500	0.88	0.86	0.90	0.86	0.96	0.95	0.13	0.99	0.79	1.00	0.97	0.95	--
600	0.82	0.81	0.85	0.81	0.91	0.93	--	0.93	0.79	1.00	0.95	0.87	--
650	0.81	0.79	0.84	0.79	0.89	0.91	--	0.90	0.79	1.00	0.94	0.85	--
700	0.80	0.77	0.82	0.77	0.87	0.88	--	0.88	0.79	1.00	0.93	0.83	--
750	0.78	0.75	0.81	0.75	0.86	0.86	--	0.86	0.79	1.00	0.93	0.65	--
800	0.76	0.74	0.80	0.74	0.84	0.82	--	0.84	0.79	1.00	0.93	0.54	--
850	0.75	0.72	0.79	0.72	0.84	0.52	--	0.83	0.79	0.99	0.93	0.44	--
900	0.73	0.71	0.78	0.71	0.83	0.49	--	0.82	0.76	0.95	0.93	0.33	--
950	0.72	0.69	0.77	0.69	0.81	0.43	--	0.81	0.71	0.95	0.93	0.23	--
1000	0.69	0.67	0.77	0.67	0.81	0.32	--	0.80	0.48		0.93	--	--
1050	0.61	0.65	0.73	0.65	0.70	0.32	--	0.68	0.48	0.42	0.93	--	--
1100	0.49	0.61	0.62	0.61	0.55	0.32	--	0.55	0.48	0.27	0.69	--	--
1150	0.39	0.53	0.49	0.52	0.41	0.32	--	0.47	0.48	0.20	0.57	--	--
1200	0.30	0.38	0.37	0.38		--	--		--	--	0.36	--	--
1250	0.24	0.28	0.28	0.28	0.32	--	--	0.36	--	--	0.36	--	--
1300	--	0.21	0.21	0.21	0.25	--	--	0.29	--	--	0.36	--	--
ASTM Form	A269 Pipe	A269 Pipe	A269 Pipe	A269 Pipe	A312 Pipe	A268 Pipe	B68 Tube	B622 Pipe	B165 Pipe	B167 Pipe	B443 Pipe	BA53 Pipe	B210 Pipe

* Do not use for temperatures lower than 32°F.

BECAUSE WE CONTINUALLY EXAMINE WAYS TO IMPROVE OUR PRODUCTS, WE RESERVE THE RIGHT TO ALTER SPECIFICATIONS WITHOUT NOTICE.